

TA12
**TEMAPRIME EE
TEMALAC FD 80**

The alkyd systems TA12 are suitable for steel, aluminium and zinc surfaces exposed to climatic conditions. The primer of the system, TEMAPRIME EE is a fast drying primer with excellent anticorrosive properties. The systems are suitable for application in painting shops.

Corrosivity categories/durability according to ISO 12944
Tikkurila Oyj code Treatment
Steel surfaces
A2.01
Corrosivity categories/durability C2-L

Steel constructions, machinery and equipment indoors.
According to SFS 5873, system F20.01

TA12

 TEMAPRIME EE
TEMALAC FD 80

AK80/2-FeSa2½

 40 µm
40 µm
80 µm
DFT

A1.03, A3.01
Corrosivity categories/durability C2-H, C3-L

Steel constructions in cold indoor spaces and outdoors in clean rural environment. E.g. frameworks and platforms in warehouses and work shops.

TA12

 TEMAPRIME EE
TEMALAC FD 80

AK120/2-FeSa2½

 80 µm
40 µm
120 µm
DFT

A1.04, A2.03, A3.02
Corrosivity categories/durability C2-H, C3-M

Steel constructions, machinery and equipment outdoors in urban, maritime and industrial environment. E.g. outside of tanks and different kinds of steel structures.

TA12

 TEMAPRIME EE
TEMALAC FD 80

AK160/3-FeSa2½

 80 µm
80 µm
160 µm
DFT

Marking of paint systems: TA12-SFS-EN ISO 12944-5/A3.01 (AK120/2-FeSa2½)
Aluminium surfaces
Corrosivity categories C1, C2, C3-M

Aluminium surfaces outdoors in urban, maritime and industrial environment. Surfaces indoors exposed to mild gas and chemical dust.

TA12

 TEMAPRIME EE
TEMALAC FD 80

AK80/2-AISaS

 40 µm
40 µm
80 µm
DFT

Zinc surfaces
A7.06
Corrosivity categories/durability C3-M

Zinc surfaces outdoors in urban, maritime and industrial environment.
Surfaces indoors exposed to mild gas and chemical dust.

TA12

 TEMAPRIME EE
TEMALAC FD 80

AK120/2-ZnSaS

 80 µm
40 µm
120 µm
DFT

COLOURS

The product is tintable with TEMASPEED colorants, thus ensuring the possibility to get shades from RAL-, BS-, NCS- and other colour cards.

SUITABLE SHOP PRIMERS

TEMABLAST EV 110, epoxy shop primer.
TEMAWELD ZSM, zinc silicate.

SURFACE PREPARATION

Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)

Steel surfaces:

Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.

Zinc surfaces:

Sweep blast-clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with PANSSARIPESU detergent.

Hot dip galvanized surfaces are recommended to be painted with a misty coat (paint thinned 25 - 30 %) before the actual priming.

Damages in the zinc coating have to be repaired with TEMAZINC 99, a zinc rich epoxy paint. Before painting, clean the surfaces thoroughly (Sa2½/St3) and level off the edges around the cleaned areas.

Aluminium surfaces:

Sweep blast-clean with none-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with MAALIPESU detergent.

APPLICATION CONDITIONS

The surface must be clean and dry and the surface temperature should remain at least 3 °C above the dew point. During application and drying the temperature of the air, paint and surface should be a minimum of +5 °C. The relative humidity should not exceed 85 %.

APPLICATION

The paint should be mixed thoroughly before application and then applied in an even coat on the dry and clean surface. Application with airless or conventional spray, brush or roller. Stripe coating of sharp edges, welding seams etc. should be done by brush or roller.

MAINTENANCE PAINTING**Maintenance**

Touch-up painting is sufficient for maintenance when the rust grade is Ri1 - Ri3. (ISO 4628-3)

Damages caused by transport or installation may also be repaired by touch-up painting. Remove all loose paint, clean rusty areas according to system demands. On steel surfaces small areas can be grinded or wire brushed to preparation grade St2. (SFS-ISO 8501-1)

Level off the edges between the old paint film and the cleaned up areas. When using blast cleaning, be sure that there are no cracks in the remaining paint film. If the entire surface has to be overcoated, abrade the old topcoat to a rough finish. Remove all dust and other cleaning residues. Apply primers and finish according to the original paint system, qualities and film thicknesses.

Repainting

When the rust grade is Ri4 or Ri5, the entire coating must be renewed. Remove the old paint film and clean the surfaces to preparation grade Sa2½. Recoat in accordance with the original paint system.

PRODUCT INFORMATION

More detailed product information is available in respective data sheets.

ttp100209

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not accept any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.